

## STANDARD INFORMATION

**Standard Number:** CSA B137.2

**Standard Name:** Polyvinylchloride (PVC) Injection Moulded Gasketed Fittings for Pressure Applications

**Standard Edition and Issue Date:** 6<sup>th</sup> Edition Dated January 1, 2017

**Date of Revision:** January 1, 2017

**Date of Previous Revision of Standard:** 5<sup>th</sup> Edition Revised January 1, 2016

## EFFECTIVE DATE OF NEW/REVISED REQUIREMENTS

**Effective Date:** **February 16, 2019**

## IMPACT, OVERVIEW, AND ACTION REQUIRED

**Impact Statement:** A review of all Listing Reports is necessary to determine which products comply with new/revised requirements and which products will require re-evaluation. **NOTE:** Effective immediately, this revised standard will be exclusively used for evaluation of new products unless the Applicant requests in writing that current requirements be used along with their understanding that their listings will be withdrawn on Effective Date noted above, unless the product is found to comply with new/revised requirements.

### Overview of Changes:

- Added sizes 6 x 6 and 8 x 6 NPS for anchor Tees
- Added test for Liquid immersion with IRM 903 oil
- Added requirements for oil resistant gasket

Specific details of new/revised requirements are found in table below.

**If the applicable requirements noted in the table are not described in your report(s), these requirements will need to be confirmed as met and added to your report(s) such as markings, instructions, test results, etc. (as required).**

### Client Action Required:

**Information** – To assist our Engineer with review of your Listing Reports, please submit technical information in response to the new/revised paragraphs noted in the attached or explain why these new/revised requirements do not apply to your product (s).

***Current Listings Not Active? – Please immediately identify any current Listing Reports or products that are no longer active and should be removed from our records. We will do this at no charge as long as Intertek is notified in writing prior to the review of your reports.***



## STANDARD INFORMATION

CLAUSE	VERDICT	COMMENT
--------	---------	---------

Additions to existing requirements are underlined and deletions are shown ~~lined out~~ below.

### Physical properties of standard and oil resistant elastomeric gaskets for pressure fittings

Table 3

Property	Conditions	ASTM test method	Requirements (standard gasket)	Requirements (oil resistant gasket)
<u>Liquid immersion</u> <u>903 Oil</u>	<u>Immersion period</u> <u>70 h at 70 ± 2 °C</u>	<u>D471</u>	=	<u>Maximum of 50%</u> <u>change in volume</u>

CUSTOMERS PLEASE NOTE: This Table and column “Verdict” can be used in determining how your current or future production is or will be in compliance with new/revised requirements.